

Evolve

RECYCLED. NO COMPROMISE.

PRODUCT SPECIFICATIONS : EVOLVE EVERYDAY

Parameter	Methods	Values
Basis weight (g/m ²)	ISO 536	80
Thickness (µm)	ISO 534	105
Whiteness CIE	ISO 11475	150
D65 Brightness (%)	ISO 2470	104
Opacity (%)	ISO 2471	> 94
Moisture content (%)	ISO 287	4.5
Bendtsen roughness (ml/min)	ISO 8791-2	160
Kodak Stiffness MD (mN.m)	ISO 5629	0.36
Kodak Stiffness CD (mN.m)		0.14
Bending Stiffness MD (mN)	ISO 2493	80
Bending Stiffness CD (mN)		40

These values are indicative only.
Valid from : June 2014

